



www.insolcorp.com

18 C° Infinite R Energy Sheet

M70 16" x 4ft Sheets

101.18R07016048

COMPONENT	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Film	multilayer white polyfilm	4.4 mil	.1118 mm
Pocket	formed white polyfilm pocket	~35 ct 1.5"x 2.0" x .25" PCM filled pods per Ft ²	376 ct 38mm x 51mm x 6mm PCM filled pods per M ²
PCM	Proprietary Blend of Inorganic Phase Change Materials	~1.0 lbs phase change materials per Ft ²	~4.89 kilograms per sq. meter

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
M-Value	ASTM	70 BTU per sq. ft.	221 W per sq. meter
Melt Point	DSC	65.0° Fahrenheit	18° Celsius
Specific Heat	DSC	1.35 BTU/lb	~3.14 kj/kg
Latent Heat	DSC	~86 btu/lb	~200 j/g
Thermal Conductivity	DSC	~0.16 W/ft/K Liquid ~0.33 W/ft/K Solid	~0.54 W/m/K Liquid ~1.09 W/m/K Solid
Dimensions	Ruler	16.5" x 48"	622mm X 1219mm
Total Unit Thickness	Micrometer	.25"	6mm
Weight	Scale	0.75 lbs per sq. ft.	3.42 kg per sq. meter
Permeability	ASTM E96	0.08 (grains/hr*ft ² *in Hg)	4.60 ng / N's

FIRE TESTING	ASTM E84	UL 723	ASTM E800 -0
Flame Spread	5	5	passed
Smoke Development	10	10	

POLYFILM PACKAGING			
PHYSICAL PROPERTIES	TEST STANDARD	VALUES (ENGLISH)	VALUES (METRIC)
Caliper	ASTM D 21203	4.4 MIL	11 mm
Yield	Calculated	65050 IN ² / Lb.	92.36 M/Kg
Puncture Resistance	MIL STD 3010	20 Lbs	9.09 Kg
Tensile Strength	ASTM D 882	28 lbs/IN	1.973 Kg/CM ²
Breaking Strength	MIL STD 3010	75Lbs/IN (GRAB)	5.285 Kg/CM ²
Water Vapor Transmission	ASTM F 1249	0.0005 G/100 IN ² Day	0.0005 G/645 CM ² Day
Seal Strength	ASTM F 88	18 Lbs/IN	1.268 Kg/CM ²
Sealing Temp	Manufacturer's Spec	400° F @ 40PSI 1.5 Sec	



3510 Cavaretta Ct., Las Vegas, NV 89103
Phone: 1-800-509-2199 info@insolcorp.com